



Light Traction Bloc Batteries

G06-06-240

(6V 240Ah @ 5hr)

Eternity Technologies valve regulated lead-acid batteries for the light traction market. With an innovative Gel-technology and maintenance free design, Eternity Technology Gel Bloc batteries are compatible with all universal cyclic applications.





Electrical Specifications

Voltage	6V
80% DOD Voltage Cutoff	5.6V
Self Discharge	Less than 3% per month (20°C/68°F)
Charge Temperature	Min: -10°C (14°F) / Max: 50°C (122°F)
Discharge Temperature**	Min: -40°C (-40°F) / Max: 50°C (122°F)
Storage	Min: -20°C (-4°F) / Max: 60°C (140°F)


Amp Hours (AH)						
20 HR	10 HR	5 HR	3HR	2HR	1HR	
270	284	240	222	208	168	

^{**} CAUTION: Depths of discharge, operating voltages and currents, when designing systems for use at maximum temperatures, will vary.

Mechanical Specifications


Industry Reference	305			
Length (A)	11.7 in	298 mm		
Width (B)	7.0 in	178 mm		
Height (C)	13.6 in	346 mm		
Height (D)	13.7 in	349mm		
Weight	105 lbs	48 kgs		
Terminal (Opt'l)*	M8			
Cell(s)	3			
Electrolyte	Gel			
Terminal Torque Nm	8			

NOTE: There is a tolerance of +/-2%.





Left - positive



Right - negative

Features

Maintenance-free bloc batteries in Gel technology (no topping up during lifetime)

Good high current performance for extreme operating conditions

High-class patented safety valve

700 cycles (DIN EN 60254-1) (IEC 254-1)

Valve-regulated lead-acid battery

Recyclable

Long cycle life

Classified as a non-spillable battery is not restricted for trabsportation by:

- Air (IATA/ICAO provision 67)
- Ground (STB, DOT-CFR-HMR49)
- Water (IMDG amendment 27)

Applications

Electric vehicles

Wheelchairs

Cleaning machines

Electric working platforms

Universal for multiple cyclic applications

Compliant with EN60254-1&IEC254-1

^{*} Including A-Terminal

Charging profile

 $\textbf{IU Charging} \hspace{1cm} \textbf{I} = min. \, 12\% \, C_5 \, max. \, 18\% \, C_5$


U = 2.4 V per cell

IUI Charging $I_1 = min. 12\% C_5 max. 18\% C_5$


 $U = 2.35 \, \text{V} \, \text{per cell}$

 $I_2 = 1.5 \% C_5$ for max. 4 hours


Self discharge at different temperatures



Capacity vs. temperature



Relation between charging, voltage and temperature



Storage: Determine the state of charge

