Eternity TECHNOLOGIES

Light Traction Bloc Batteries

G06-12-170-3

(12V 177Ah @ 5hr)

Eternity Technologies valve regulated lead-acid batteries for the light traction market. With an innovative Gel-technology and maintenance free design, Eternity Technology Gel Bloc batteries are compatible with all universal cyclic applications.



B Part of our Bloc Batteries range

Positive



Negative

Features

- Maintenance-free bloc batteries in Gel technology (no topping up during lifetime)
- Good high current performance for extreme operating conditions
- High-class patented safety valve
- 700 cycles (DIN EN 60254-1) (IEC 254-1)
- Valve-regulated lead-acid battery
- Recyclable
- Long cycle life
- Low self discharge rate allows for up to 2 years shelf life
- Classified as a non-spillable battery is not restricted for transportation by:
  - Air (IATA/ICAO provision 67)
  - Ground (STB, DOT-CFR-HMR49)
  - Water (IMDG amendment 27)

Electrical Specifications

Voltage	12V
80% DOD Voltage Cutoff	11.2V
Self Discharge	Less than 3% per month (20°C/68°F)
Charge Temperature	Min: -10°C (14°F) / Max: 50°C (122°F)
Discharge Temperature**	Min: -40°C (-40°F) / Max: 50°C (122°F)
Storage	Min: -20°C (-4°F) / Max: 60°C (140°F)

Amp Hours (AH)					
20 HR	**10 HR**	**5 HR**	**3 HR**	**2 HR**	**1 HR**
212	200	177	166	157	145

** CAUTION: Depths of discharge, operating voltages and currents, when designing systems for use at maximum temperatures, will vary.

Mechanical Specifications

Industry Reference	DIN C	
Length (A)	20.4 in	518 mm
Width (B)	10.8 in	274 mm
Height (C)	9.4 in	238 mm
Weight	150 lbs	68 kgs
Terminal (Opt'l)*	A-Pole (Industrial Terminal optional)	
Cell(s)	6	
Electrolyte	Gel	
Terminal Torque Nm	n/a	

NOTE: There is a tolerance of +/-2%.

Applications

- Electric vehicles
- Wheelchairs
- Cleaning machines
- Electric working platforms
- Universal for multiple cyclic applications

Compliant with

EN60254-1&2 & IEC254-1/2
ISO 7176-25 SAE J 1495

Charging profile

IU Charging
I = min. 12% C_5 max. 18% C_5
U = 2.4 V per cell

IUI Charging
I_1 = min. 12% C_5 max. 18% C_5
U = 2.35 V per cell
I_2 = 1.5 % C_5 for max. 4 hours

Self discharge at different temperatures



Capacity vs. temperature



Relation between charging, voltage and temperature



Storage: Determine the state of charge